

Features & Benefits

- Various range of Thermal Conductivity and Resistance
- High Voltage Breakdown
- Adhesive strength surfaces
- High temperature applications
- Proven Long term reliability
- Thermal Curing at elevated temperature
- RoHS compliant, Halogen free and lead-free process
- Non-silicone based with zero outgassing

Thermal Set Pad is an epoxy base thermal conductive and electrical isolating material (B stage) which requires heat curing that is ideal for high power density application.

Applications

- High power density applications which required low thermal resistance
- Industrial Motor, servo motor and EV motor
- LED modules
- Power Supplies and Semiconductors packaging
- Household appliances and consumer electronics

Configurations and Storage Conditions

The TCI family comes in 3 different thermal performance products:

TSP-3, TSP-8, TSP 12

- Refrigeration <10°C for 3 months from manufacturing date
 - Available in Rolls, Sheets, custom sizes.
 - Packaging in Bulk, Trays or Tape & Reel.

We provide custom solutions for your applications. For further inquiries, please contact your local sales agent or directly to TCLAD sales in your region.



Property	Method (Units)	TSP-3 (Typ.)	TSP-8 (Typ.)	TSP-12 (Typ.)
Resin Base	Chemistry	Epoxy	Epoxy	Epoxy
Color	Visual	Gray	Gray	Gray
Hardness	ASTM D2240 (Shore A)	96	96	96
Thermal Conductivity	TO220 (W/mK)	3	8	12
Thermal Conductivity	ASTM D5470 (W/mK)	1.5	2.5	3.0
Thermal Resistance	ASTM D5470 (°C/W)	0.11 (100 μm)	0.08 (100 μm)	0.05 (100 μm)
		0.18 (160 μm)	0.12 (160 μm)	0.08 (160 μm)
		0.21 (200 μm)	0.15 (200 μm)	0.10 (200 μm)
Density	ASTM D792 (g/cm3)	2.69	2.72	3.22
Operating Temperature Range	- (°C)	-40°C to 150°C	-40°C to 150°C	-40°C to 150°C
Breakdown Voltage	ASTM D149 JIS C2110 (AC KV/mm)	20	20	20
Dielectric Constant	IPC-TM-6502.5.5.1	7.04	8.04	8.4
Dielectric Loss Tangent	IPC-TM-6502.5.5.1	0.0232	0.0294	0.0170
Volume Resistivity	IPC-TM-6502.5.17.1 (Ω.cm)	1 x 10 ¹³	1 x 10 ¹³	1 x 10 ¹³
Peel Strength	JIS C6481 (Kgf/cm)	>1.2	>1.2	>1.2
Curing Temperature	< 5 min (°C)	120	120	120
Shelf Life	Storage Temp <10°C (months)	3	3	3
Flame Rating	UL	E541520	E541520	TBD

TCLAD

US Sales.us@tclad.com
 APAC Sales.asia@tclad.com
 Europe Sales.eu@tclad.com
www.tclad.com



All statements, technical information and recommendations herein are based on tests we believe to be reliable, and THE FOLLOWING IS MADE IN LIEU OF ALL WARRANTIES OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF MARKET ABILITY AND FITNESS FOR PURPOSE. Sellers' and manufacturers' only obligation shall be to replace such quantity of the product proved to be defective. Before use, user shall determine the suitability of the product for its intended use, and the user assumes all risk and liability whatsoever in connection therewith. NEITHER SELLER NOR MANUFACTURER SHALL BE LIABLE EITHER IN TORT OR IN CONTRACT FOR ANY LOSS OR DAMAGE DIRECT, INCIDENTAL, OR CONSEQUENTIAL, INCLUDING LOSS OF PROFITS OR REVENUE ARISING OUT OF THE USE OR THE INABILITY TO USE THE PRODUCT. No statement, purchase order or recommendation by seller or purchaser not contained herein shall have any force or effect unless in an agreement signed by the officers of the seller and manufacturer. All marks used above are trademarks and/or registered trademarks of TCLAD Inc and its affiliates in the U.S., Germany and elsewhere. © 2021 TCLAD Inc. All rights reserved. US



Rev 2024-D20-004