

### Thermal Conductive Filler Liquid

TCFL 8.0

## Features & Benefits

- 8.0 W/mK Thermal Conductivity
- Electrically Isolating
- Low Interfacial Resistance
- Superior Thermal Performance

## Applications

- Automotive Electronics (HEV, NEV, Batteries)
- PCBA to heatsink
- Discrete components to heat spreader
- Fiber optics and Telecom equipment

## Introduction

**TCLAD TCFL** is a thermally conductive gap filling material that is offered in a two-part material. The purpose of the material is to minimize thermal resistance between the heat source and the heat sink or heat spreader. Depending on application the material is available in different viscosity and hardness.

**Typical properties** of gap filling materials have the following characteristics: Thermal conductivity, viscosity, hardness, pot life, volume resistivity etc. It is typically offered in cartridges, or containers and can be dispensed through a static mixing nozzle with a handheld dispensing gun or by automated dispensing equipment.

**Mixing** the two parts into a single material, the liquid form cures into a solid form depending on the curing time and temperature. Before the material cures into a solid form, the material should be placed in the interface and put into compression so that it can form around the surrounding surfaces to remove as much air and to wet out to the adjoining surfaces as much as possible.

**How to use:** Depending on storage time the material is stored from the date on manufacture, premixing prior to use may be required. Mix part A and B 1:1 and apply mixture to the surface. Apply pressure to remove the air gap as much as possible to improve heat dissipation.

**Processing:** After the material is exposed to air it will begin to cure. At room temperature. Curing can be accelerated by increasing the temperature.

**Useable life and storage:** TCFL products are best if stored in a cool and dry / non-humid environment, especially where it is not exposed to any sunlight. Containers that have been stored for longer than two months should be remixed with a clean mixer and vacuum to prevent air entrapment. Whereas the cartridge containers should be flipped upside down every two weeks to prevent the particle fillers from settling to the bottom. The shelf life can be up to 6 months when properly stored.

**Package Information:** Typical package size, cartridges: 50cc, and 400 cc. Containers: 20L and 200L or 1Kg and 200Kg. Custom size available.

**Precautions:** Please review the technical datasheet of the material before use of the products in terms of the material characteristic to fit one's application. All values stated here are typical values.

We provide custom solutions for your applications. For further inquiries, please contact your local sales agent or directly TCLAD in your region.

## TCLAD

US [Sales.us@tclad.com](mailto:Sales.us@tclad.com)  
APAC [Sales.asia@tclad.com](mailto:Sales.asia@tclad.com)  
Europe [Sales.eu@tclad.com](mailto:Sales.eu@tclad.com)  
[www.tclad.com](http://www.tclad.com)



All statements, technical information and recommendations herein are based on tests we believe to be reliable, and THE FOLLOWING IS MADE IN LIEU OF ALL WARRANTIES OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF MARKET ABILITY AND FITNESS FOR PURPOSE. Sellers' and manufacturers' only obligation shall be to replace such quantity of the product proved to be defective. Before use, user shall determine the suitability of the product for its intended use, and the user assumes all risk and liability whatsoever in connection therewith. NEITHER SELLER NOR MANUFACTURER SHALL BE LIABLE EITHER IN TORT OR IN CONTRACT FOR ANY LOSS OR DAMAGE DIRECT, INCIDENTAL, OR CONSEQUENTIAL, INCLUDING LOSS OF PROFITS OR REVENUE ARISING OUT OF THE USE OR THE INABILITY TO USE THE PRODUCT. No statement, purchase order or recommendation by seller or purchaser not contained herein shall have any force or effect unless in an agreement signed by the officers of the seller and manufacturer. All marks used above are trademarks and/or registered trademarks of TCLAD Inc and its affiliates in the U.S., Germany and elsewhere. © 2021 TCLAD Inc. All rights reserved. US



Rev 2025-D66-001

Item	Condition	Unit	Value	Method
<b>General</b>				
Color	Visual	-	A: Yellow B: White	1:1
Continuous Use Temp	-	°C	-50 ~ 200	-
Viscosity (Mix)	25°C	cps	450,000	ASTM D2196
Density	25°C	g/cc	3.3	ASTM D792
Hardness	Shore	00	60	ASTM D2240
<b>Electrical</b>				
Dielectric Constant	1 GHz	-	8.3	ASTM D150
Dielectric Strength	-	kV/mm	8	ASTM D149
Volume Resistivity	-	Ω cm	> 1×10 <sup>13</sup>	ASTM D257
<b>Thermal</b>				
Thermal Conductivity	-	W/m-K	8.0	ASTM D5470
<b>Cure Schedule</b>				
Pot life @ 25°C	2x viscosity	Hours	2	
Cure @ 25°C	Oven	Hours	24	
Cure @ 100°C	Oven	Minutes	10	
<b>Durability</b>				
RoHS	-	-	Compliant	
Flame Rating	Vertical Burn Test	-	V-0	UL94

### Applications Tips:

- **Correct Mixing Ratio:** Ensure that both components (Part A and Part B) are mixed in the correct ratio (1:1) for optimal performance and reliable results.
- **Surface Preparation:** Thoroughly clean the surfaces before applying the liquid gap filler to ensure proper adhesion and to maximize thermal performance.
- **Consistent Mixing:** For consistent results, especially in high-volume applications, use a static mixer or an automatic mixing machine.
- **Curing Time:** Allow the gap filler to fully cure before subjecting the components to any mechanical stress, ensuring long-lasting effectiveness.
- **Proper Storage:** Store any unused materials in a cool, dry location and adhere to the manufacturer's guidelines for shelf life and storage conditions to maintain product integrity.