

Method

MET 5.4-01-

40000

ASTM D5470

ASTM D5470

MET 5.4-01-

40000

IPC-TM-650 2.5.5.

IPC-TM-650 2.5.5.9

IPC-TM-650 2.5.5.9

Value

7.5

3.0

0.13 (0.02)

0.17 (0.026)

0.20 (0.031)

0.25 (0.039)

0.30

0.40

0.47

0.58

4.2

0.015

36



Features & Benefits

- Thermal resistance 38µm, 0.13°C-cm²/W (0.02°C-in²/W)
 - (38μm thickness)
- Product Thermal conductivity of 7.5 W/m-K
 - o (2oz Cu x 38μm HPL x 1.6 Al)
- High Voltage Strength
- High temperature applications
- Lead-free solder compatible
- Eutectic AuSn compatible
- RoHS compliant and environmentally green
- Available on aluminum and copper base substrates
 - Other substrate materials may be available.

Thermal Clad Metal Core PCB's (MCPCB's) minimize thermal impedance and conducts heat more efficiently than standard printed wiring boards (PWB's). These substrates are more mechanically robust than Direct Bond Copper (DBC) construction.

The differentiating technology of Thermal Clad resides in the dielectric. This datasheet highlights the performance characteristics of Thermal Clad HPL dielectric.

Applications

- · High power density applications where achieving low thermal resistance is
- · Automotive high voltage power modules
- Power conversion
- LED headlight & foglamps
- High power LED architectural lighting and UV LED
- Motor drives
- Solid state relays

Configurations

	Base Metal	Thickness mm (mil)
•	5052 Aluminum	0.8 (32), 1.0 (40)*, 1.5 (59)*, 2.0 (80), 3.2 (125)
•	6061 Aluminum	0.8 (32), 1.0 (40)*, 1.5 (59)*, 2.0 (80), 3.2 (125), 4.8 (190
•	4045 Aluminum	1.5 (59), 2.0 (80)
•	Copper C1100	0.5 (20), 0.8 (32), 1.0 (40)*, 1.58 (62)*, 3.2 (125)
	Copper Foil	Weight oz (thickness µm)
•	ED Copper:	1oz (35), 2oz (70), 3oz (105), 4oz (140), 6oz (210)
•	RA Copper:	8oz (280), 10oz (350)

- Most common thicknesses.
- Other thicknesses and alloys may be available. Please contact TCLAD sales. department for more information.



 $\Theta\left(\frac{C}{W}\right) = \frac{(T_T - T_B)}{40W \text{ typ}}$

TCLAD APAC sales.asia@tclad.com Europe sales.eu@tclad.com www.tclad.com



pΕ Capacitance mil) 1014 ASTM D257 Volume Resistivity Ω -m 1013 ASTM D257 Surface Resistivity Ω/sq 38µm (1.5mil) 5.0 50µm (2mil) 7.7 Breakdown ASTM D149 **KVAC** Voltage 100µm (4mil) 12.2 150µm (6mil) 17.4 **Mechanical Properties** Color Off-white Peel Strength @ 25°C N/mm ((lb/in) 0.9(5)ASTM D2861 Glass Transition (Tg °C 185 ASTM E1356 CTE in X,Y/Z Axis <Tg μm/m°C 35 **ASTM D3386** ASTM D3386 CTE in X,Y/Z Axis >Tg 85 µm/m°C 90) Storage Modulus GPa 17/12 **ASTM D4065** Chemical Properties Water Vapor Retention % Wt. 0.11 ASTM E595 ASTM Out-Gassing Total Mass Loss % Wt. 0.15 E595 Collect Volatile Condensable % Wt. < 0.01 ASTM E595 Material Agency Ratings & Durability UL Maximum Operating °C 140 UL 746 Temperature (MOT) V-0 **UL Flammability** UL 94 ASTM D3638/ IEC UL Comparative Tracking Index (CTI) 0 / 600 °C 325 UL 746 Solder Limit Rating RoHS

Item

Thermal

Thermal

Impedance

Dissipation

Factor

Electrical Properties

Dielectric Constant

Resistance

Thermal Properties

Product Thermal Conductivity

Dielectric Thermal Conductivity

Thickness

38µm (1.5mil)

50µm (2mil)

100µm (4mil)

150µm (6mil)

50µm (2mil)

100µm (4mil)

150µm (6mil)

100µm (4mil)

100 µm (4

38µm (1.5mil)

Unit

W/m-K

W/m-K

 $^{\circ}$ C-cm 2 /W

 $(^{\circ}C-in^2/W)$

°C/W

IMHz

All statements, technical information and recommendations herein are based on tests we believe to be reliable, and THE FOLLOWING IS MADE IN LIEU OF ALL WARRANTIES OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF MARKET ABILITY AND FITNESS FOR PURPOSE. Sellers' and manufacturers' only obligation shall be to replace such quantity of the product proved to be defective. Before using, user shall determine the suitability of the product for its intended use, and the user assumed Irisk and liability whatsoever in connection therewith. NEITHER SELLER NOR MANUFACTURER SHALL BE LIABLE EITHER IN TORT OR IN CONTRACT FOR ANY LOSS OR DAMAGE DIRECT, INCIDENTAL, OR CONSEQUENTIAL, INCLUDING LOSS OF PROFITS OR REVENUE ARSINING OUT OF THE USE OR THE INABILITY TO USE THE PRODUCT. No statement, purchase order or recommendation by seller or purchaser not contained herein shall have any force or effect unless in an agreement signed by the officers of the seller and manufacturer. All marks used above are trademarks and/or registered trademarks of TCLAD Inc and its affiliates in the U.S., Germany and elsewhere.

2021 TCLAD Inc. All rights reserved. US

