

Features & Benefits

- Thermal resistance 100 μ m, 0.06 °C-in²/W
- Product Thermal conductivity of 12 W/m-K
 - (2oz Cu x 100 μ m SFL-12 x 1.5 Al)
- High Electrical Strength
- Lead-free solder compatible
- RoHS compliant and environmentally green
- **Available as a laminated panel, RCC or prepreg**
- **Available on aluminum and copper base substrates**
 - Other substrates materials may be available.

TCLAD Metal Core PCB's (MCPCB's) minimize thermal impedance and conduct heat more efficiently than standard printed wiring boards (PWB's).

The distinguishing difference of Thermal Clad resides in the dielectric. This datasheet highlights the performance characteristics of TCLAD SFL-12 dielectric.

Applications

- High power density applications where achieving low thermal resistance is required, such as:
- LED Lighting
- Power conversion
- Motor drives
- Solid state relays

Configurations

Base Metal	Thickness mm (mil)
• 5052 Aluminum	0.8 (32), 1.0 (40)*, 1.5 (59)*, 2.0 (80)
• 6061 Aluminum	0.8 (32), 1.0 (40)*, 1.5 (59)*, 2.0 (80)
• 1050 Aluminum	0.8 (32), 1.0 (40)*, 1.5 (59)*, 2.0 (80)
• 4045 Aluminum	1.5 (59), 2.0 (80)
• Copper C1100	1.0 (40)*, 1.5 (59)*, 2.0 (80)
Copper Foil	Weight oz (thickness μ m)
• ED Copper	1oz (35), 2oz (70), 3oz (105), 4oz (140), 6oz (210)
• RA	8oz (280), 10oz (350)

* Most common thicknesses

** Other thicknesses and alloys may be available.

Please contact TCLAD sales department for more information.

We provide custom solutions for your applications. For Further inquiries, please contact your local sales agent or directly to TCLAD sales in your region.

TCLAD

US Sales.us@tclad.com
 APAC Sales.asia@tclad.com
 Europe Sales.eu@tclad.com
www.tclad.com



All statements, technical information and recommendations herein are based on tests we believe to be reliable, and THE FOLLOWING IS MADE IN LUEU OF ALL WARRANTIES OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF MARKET ABILITY AND FITNESS FOR PURPOSE. Sellers' and manufacturers' only obligation shall be to replace such quantity of the product proved to be defective. Before use, user shall determine the suitability of the product for its intended use, and the user assumes all risk and liability whatsoever in connection therewith. NEITHER SELLER NOR MANUFACTURER SHALL BE LIABLE EITHER IN TORT OR IN CONTRACT FOR ANY LOSS OR DAMAGE DIRECT, INCIDENTAL, OR CONSEQUENTIAL, INCLUDING LOSS OF PROFITS OR REVENUE ARISING OUT OF THE USE, OR THE INABILITY TO USE, THE PRODUCT. No statement, purchase order or recommendation by seller or purchaser not contained herein shall have any force or effect unless in an agreement signed by the officers of the seller and manufacturer. All marks used above are trademarks and/or registered trademarks of TCLAD Inc and its affiliates in the U.S., Germany and elsewhere. © 2021 TCLAD Inc. All rights reserved. US



Rev 2024 D10-004

Item	Thickness	Unit	Value (Typ.)	Method
Thermal Properties				
Product Thermal Conductivity		W/m-K	12	TO220
Dielectric Thermal Conductivity		W/m-K	3.2	ASTM D5470
Thermal Resistance	100 μ m (4mil)	°C-in ² /W	0.06	ASTM D5470
Thermal Impedance	100 μ m (4mil)	°C/W	0.08	TO-220
Electrical Properties				
Dielectric Constant		-	4.2	IPC-TM-650 2.5.5.3
Dissipation Factor	100 μ m (4mil)	1MHz	0.011	IPC-TM-650 2.5.5.3
Capacitance	100 μ m (4mil)	pF	38	IPC-TM-650 2.5.5.3
Volume Resistivity		Ω -cm	10 ¹³	IPC-TM-650 2.5.17.1
Surface Resistivity		Ω /sq	10 ¹³	IPC-TM-650 2.5.17.1
Breakdown Voltage	80 μ m (3.2mil) 100 μ m (4mil) 150 μ m (6mil)	KVAC	4 5 7	ASTM D149
Mechanical Properties				
Color		-	Off-white	Visual
Peel Strength @ 25°C		Kg/cm	>1.3	IPC TM-650 2.4.8
Glass Transition (Tg)		°C	180	IPC TM-650 2.4.25
CTE in X,Y/Z Axis <Tg		μ m/m°C	15	IPC TM-650 2.4.24.5
CTE in X,Y/Z Axis >Tg		μ m/m°C	18	IPC TM-650 2.4.24.5
Storage Modulus @ 25°C		GPa	18	ASTM D638
Chemical Properties				
Water Vapor Retention		%	< 0.5	ASTM E595
Out-Gassing Total Mass Loss		%	< 0.1	ASTM E595
Collect Volatile Condensable Material		%	< 0.1	ASTM E595
Agency Ratings & Durability (UL: E121882)				
UL Maximum Operating Temperature (MOT)		°C	130	UL 746
UL Flammability		-	V-0	UL 94
UL Comparative Tracking Index		(CTI)	600	UL 746E