

Features & Benefits

- Thermal resistance 100μm, 0.09 °C-in²/W
- Product Thermal conductivity of 8 W/m-K ο (2oz Cu x 100μm SFLG-8 x 1.5 Al)
- Fiber glass enhanced Prepreg
- Lead-free solder compatible
- RoHS compliant and environmentally green
- Available as a laminated panel, RCC or prepreg
- Available on aluminum and copper base substrates •
 - o Other substrates materials may be available.

TCLAD Metal Core PCB's (MCPCB's) minimize thermal impedance and conducts heat more efficiently than standard printed wiring boards (PWB's).

The differentiating technology of Thermal Clad resides in the dielectric. This datasheet highlights the performance characteristics of TCLAD SFLG-8 dielectric.

Applications

- High power density applications where achieving low thermal resistance is required, such as:
- LED Lighting
- Power conversion
- Motor drives
- Solid state relays

Configurations

Base Metal

Thickness mm (mil)

- 5052 Aluminum 0.8 (32), 1.0 (40)*, 1.5 (59)*, 2.0 (80)
- 6061 Aluminum 0.8 (32), 1.0 (40)*, 1.5 (59)*, 2.0 (80)
- 1050 Aluminum 0.8 (32), 1.0 (40)*, 1.5 (59)*, 2.0 (80)
- 4045 Aluminum 1.5 (59), 2.0 (80)
- Copper C1100 1.0 (40)*, 1.5 (59)*, 2.0 (80)

Weight oz (thickness µm)


- ED Copper 1oz (35), 2oz (70), 3oz (105), 4oz (140), 6oz (210)
- RA 8oz (280), 10oz (350)

Copper Foil

- Most common thicknesses
- Other thicknesses and alloys may be available. Please contact TCLAD sales department for more information.

We provide custom solutions for your applications. For Further inquiries, please contact your local sales agent or directly to TCLAD sales sales@tclad.com

Test Thermal Performance of Insulated Metal Substrate (IMS®) TO-220 Set-up





www.tclad.com



All statements, technical information and recommendations herein are based on tests we believe to be reliable, and THE FOLLOWING IS MADE IN LIEU OF ALL WARRANTIES OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF MARKET ABILITY AND FITNESS FOR PURPOSE. Sellers' and manufacturers' only obligation shall be to replace such quantity of the product proved to be defective. Before using, user shall determine the suitability of the product for its intended use, and the user assumes all risk and liability whatsoever in connection therewith. NETHER SELLER NOR MANUFACTURER SHALL BE LIABLE EITHERIN TORT OR INCONTRACT FOR ANY LOSS OR DAMAGE DIRECT. INCIDENTAL, OR CONSEQUENTIAL, INCLUDING LOSS OF PROFITS OR REVENUE ARISING OUT OF THE USE OR THE INABILITY TO USE THE PRODUCT. No statement, purchase order or recommendation by seller or purchaser not contained herein shall have any force or effect unless in an agreement signed by the officers of the seller and manufacturer. All marks used above are trademarks and/or registered trademarks of TCLAD Inc and its affiliates in the U.S., Germany and elsewhere. Ø 2021 TCLAD inc. All right sreemed. US



SFLG-8 Dielectric

ltem	Thickness	Unit	Value (Typ.)	Method
Thermal Pr	operties			
Product Thermal Conductivity		W/m-K	7.6	TO220
Dielectric Thermal Conductivity		W/m-K	1.85	ASTM D5470
r nermai Resistance r nermai	100µm (4mil)	°C-in²/W	0.09	ASTM D5470
Impedance	I00μm (4mil)	°C/W	0.15	TO-220
Electrical P	roperties			
Dielectric Const	ant	-	6.1	IPC-TM-650 2.5.5.3
Dissipation Factor	l 00µm (4mil)	1MHz	0.016	IPC-TM-650 2.5.5.3
Capacitance	100µm (4mil)	рF	20.8	IPC-TM-650 2.5.5.3
Volume Resistivity		Ω-cm	1013	IPC-TM-650 2.5.17.1
Surface Resistivity		Ω/sq	1015	IPC-TM-650 2.5.17.1
Breakdown Voltage	80µm (3.2mil)		4	
	l 00μm (4mil)	KVAC	5 7	ASTM D149
Mechanical	150µm (6mil) Properties		,	
Color		-	Off-white	Visual
Peel Strength @ 25°C		Kg/cm	>1.4	IPC TM-650 2.4.8
Glass Transition (Tg)		°C	150	IPC TM-650 2.4.25
CTE in X,Y/Z Axis <tg< td=""><td>µm/m°C</td><td>28</td><td>IPC TM-650 2.4.24.5</td></tg<>		µm/m°C	28	IPC TM-650 2.4.24.5
CTE in X,Y/Z Axis >Tg		µm/m°C	35	IPC TM-650 2.4.24.5
Youngs Modulus		GPa	30	ASTM D638
Chemical P	roperties			
Water Vapor Retention		%	< 0.5	IPC TM-650 2.6.2.1
Out-Gassing Total Mass Loss		%	< 0.1	ASTM E595
Collect Volatile Condensable Material		%	< 0.1	ASTM E595
Material		78		
	ings & Durabili		1882	
	ings & Durabili		1882 140	UL 746
Agency Rat	ings & Durabili	ty UL: EI2		

