

Features & Benefits

- Thermal Impedance 3mil, 0.05°C-in²/W (0.32°C-cm²/W)
- Product Thermal conductivity of 4.1 W/m-K
- High Voltage Strength
- High temperature applications
- Lead-free solder compatible
- Eutectic AuSn compatible
- RoHS compliant and environmentally green
- Available on aluminum and copper base substrates
 - Other substrates materials may be available

Thermal Clad Metal Core PCB's (MCPCB's) minimize thermal impedance and conducts heat more efficiently than standard printed wiring boards (PWB's). These substrates are more mechanically robust than Direct Bond Copper (DBC) construction.

The differentiating technology of Thermal Clad resides in the dielectric. This datasheet highlights the performance characteristics of Thermal Clad HT dielectric

Applications

- High power density applications where achieving low thermal resistance is required
- Power conversion
- Heat Rails
- Solid state relays

Configurations

Base Metal Thickness mm (mil)


- 5052 Aluminum 0.8 (32), 1.0 (40)*, 1.5 (59)*, 2.0 (80), 3.2 (125)
- 6061 Aluminum 0.8 (32), 1.0 (40)*, 1.5 (59)*, 2.0 (80), 3.2 (125), 4.8 (190)
- 4045 Aluminum 1.5 (59), 2.0 (80)
- Copper C1100 0.5 (20), 0.8 (32), 1.0 (40)*, 1.5 (60)*, 3.2 (125)

Copper Foil Weight oz (thickness µm)

- ED Copper: 1oz (35), 2oz (70), 3oz (105), 4oz (140), 6oz (210)
- RA Copper: 8oz (280), 10oz (350)

* most common thicknesses

** other thicknesses and alloys may be available. Please contact TCLAD sales department



TCLAD

US sales.us@tclad.com
 APAC sales.asia@tclad.com
 Europe sales.eu@tclad.com
www.tclad.com



All statements, technical information and recommendations herein are based on tests we believe to be reliable, and THE FOLLOWING IS MADE IN LIEU OF ALL WARRANTIES OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF MARKET ABILITY AND FITNESS FOR PURPOSE. Sellers' and manufacturers' only obligation shall be to replace such quantity of the product proved to be defective. Before use, user shall determine the suitability of the product for its intended use, and the user assumes all risk and liability whatsoever in connection therewith. NEITHER SELLER NOR MANUFACTURER SHALL BE LIABLE EITHER IN TORT OR IN CONTRACT FOR ANY LOSS OR DAMAGE DIRECT, INCIDENTAL, OR CONSEQUENTIAL, INCLUDING LOSS OF PROFITS OR REVENUE ARISING OUT OF THE USE OR THE INABILITY TO USE THE PRODUCT. No statement, purchase order or recommendation by seller or purchaser not contained herein shall have any force or effect unless in an agreement signed by the officers of the seller and manufacturer. All marks used above are trademarks and/or registered trademarks of TCLAD Inc and its affiliates in the U.S., Germany and elsewhere. © 2021 TCLAD Inc. All rights reserved. US

HT Dielectric

Item	Thickness	Unit	Value	Method
Thermal Properties				
Product Thermal Conductivity		W/m-K	4.1	MET 5.4-01-40000
Dielectric Thermal Conductivity		W/m-K	2.2	ASTM D5470
Thermal Impedance	75µm (3mil)	°C-cm²/W (°C-in²/W)	0.32 (0.05)	ASTM D5470
	100µm (4mil)		0.49 (0.077)	
	150µm (6mil)		0.71 (0.11)	
	225µm (9mil)		1.03 (0.16)	
Thermal Resistance	75µm (3mil)	°C/W	0.45	MET 5.4-01-40000
	100µm (4mil)		0.53	
	150µm (6mil)		0.70	
	225µm (9mil)		0.90	
Electrical Properties				
Dielectric Constant		-s	7	ASTM D150
Dissipation Factor	75µm (3mil)	1KHz/1MHz	0.0033/0.0148	ASTM D150
	100µm (4mil)		TBD	
	150µm (6mil)		0.0038/0.0129	
	225µm (9mil)		0.0040/0.0130	
Capacitance	75µm (3mil)	pF/cm² (pF/in²)	85 (540)	ASTM D150
	100µm (4mil)		71 (450)	
	150µm (6mil)		43 (270)	
	225µm (9mil)		25 (160)	
Volume Resistivity		Ω-m	10¹⁴	ASTM D257
Surface Resistivity		Ω/sq	10¹³	ASTM D257
Breakdown Voltage	75µm (3mil)	KVAC	8.5	ASTM D149
	100µm (4mil)		9.3	
	150µm (6mil)		11.0	
	225µm (9mil)		20	
Mechanical Properties				
Color		-	White	Visual
Peel Strength @ 25°C		N/mm ((lb/in)	1.1 (6)	ASTM D2861
Glass Transition (Tg)		°C	150	ASTM E1356
CTE in X,Y/Z Axis <Tg		µm/m°C	25	ASTM D3386
CTE in X,Y/Z Axis >Tg		µm/m°C	95	ASTM D3386
Storage Modulus		GPa	16/7	ASTM D4065
Decomposition Temperature (2% loss)		°C	370	IPC TM-650 2.4.24.6
Decomposition Temperature (5% loss)		°C	420	IPC TM-650 2.4.24.6
Chemical Properties				
Water Vapor Retention		% Wt.	0.24	ASTM E595
Out-Gassing Total Mass Loss		% Wt.	0.28	ASTM E595
Collect Volatile Condensable Material		% Wt.	0.01	ASTM E595
Agency Ratings & Durability UL: E121882				
UL Maximum Operating Temperature (MOT)		°C	140	UL 746
UL Flammability		-	V-0	UL 94
UL Comparative Tracking Index		(CTI)	0/600	ASTM D3638/ IEC 60112
Solder Limit Rating		°C	325	UL 746

