Technical Data

MP Dielectric



FEATURES & BENEFITS

- Thermal resistance 3mil, 0.09°C-in²/W (0.58°C-cm²/W)
- Product Thermal conductivity of 2.4 W/m-K
- High voltage strength
- Lead-free solder compatible
- RoHS compliant and environmentally green
- Available with aluminum and copper base
 - Other substrates materials may be available 0

Thermal Clad Metal Core PCB's (MCPCB's) minimize thermal impedance and conducts heat more efficiently than standard printed wiring boards (PWB's).

The differentiating technology of Thermal Clad resides in the dielectric. This datasheet highlights the performance characteristics of Thermal Clad MP dielectric.

Applications

- High power density applications where achieving low thermal resistance is required
- Power conversion
- Heat Rails
- Solid state relays
- Motor drives
- LED Lighting

Base Metals

Thicknesses mil (mm)

- 5052 Aluminum 32(0.8), 40(1.0)*, 63(1.6)*, 80(2.0), 125(3.2)
- 6061 Aluminum 32(0.8), 40(1.0)*, 63(1.6)*, 80(2.0), 125(3.2)
- Copper C1100 20(0.5), 32(0.8), 40(1.0)*, 60(1.5)*, 125(3.2)

Copper Foil


- ED copper 1oz, 2oz, 3oz, 4oz, 6oz
- RA 8oz, 10oz

General Model**

MP 06503 (3mil)

	THICKNESS	UNIT	VALUE	TEST METHOD
THERMAL PROPERTIES				
Product Thermal Conductivity		W/m-K	2.4	MET 5.4-01-40000
Dielectric Thermal Conductivity		W/m-K	1.3	ASTM D5470
Thermal		°C-in²/W	0.09(0.58)	ASTM D5470
Resistance	3mil (76µm)	(°C-cm ² /W)		
Thermal				
Impedance	3mil (76µm)	°C/W	0.65	MET 5.4-01-40000
ELECTRICAL PROPERTIES				
Dielectric Constant		-	6	ASTM D150
Dissipation Factor		1KHz/1MHz	0.003/0.017	ASTM D150
Capacitance	3mil (76µm)	pF/in ² (pF/cm ²)	410 (65)	ASTM D150
Volume Resistivity		Ω-m	10 ¹⁵	ASTM D257
Surface Resistivity		Ω/sq	10 ¹⁴	ASTM D257
Breakdown		1.44.0	0.5	
Voltage	3mil (76µm)	kVAC	8.5	ASTM D149
MECHANICAL PROPERTIES				
Color		-	White	Visual
Peel Strength@25°C		lb/ in (N/mm)	9 (1.6)	ASTM D2861
Glass Transition (Tg)		°C	90	ASTM E1356
CTE in XY/Z Axis <tg< td=""><td>μm /m°C</td><td>40</td><td>ASTM D3386</td></tg<>		μm /m°C	40	ASTM D3386
CTE in XY/Z Axis >Tg		μm /m°C	110	ASTM D3386
Storage Modulus(@25°C/150°C)		GPa	12 / 0.3	ASTM 4065
CHEMICAL PROPERTIES				
Water Vapor Retention		% Wt.	0.21	ASTM E595
Out-Gassing Total Mass Loss		% Wt.	0.29	ASTM E595
Collect Volatile Condensable Material		% Wt.	0.01	ASTM E595
AGENCY RATINGS & DURABILITY				
UL Maximum Operating		°C	130	UL 746
Temperature (MOT)		C	150	UL 740
UL Flammability		-	V-0	UL 94
UL Comparative Tracking Index		(CTI)	0/ 500	ASTM D3638/ IEC 60112
Solder Limit Rating		300°C/60 sec	pass	UL 746

Test Thermal Performance of Insulated Metal Substrates (IMS) TO-220 Set-up 60 lb Forc



most common thicknesses

If there is any specific inquiry other than standard specification, please contact us.

www.tclad.com



TCLAD INC Phone: +1 715-262-5898 Email: sales.us@tclad.com

ASIA-PACIFIC TCLAD TECHNOLOGY CORP. Phone: +886 3 5643931 Email: sales.asia@tclad.com

FUROPE TCLAD EUROPE GmbH Phone: +49 6352 6788210 Email: sales.eu@tclad.com All statements, technical information and recommendations herein are based on tests we believe to be reliable, and THE FOLLOWING IS MADE IN LIUE OF ALL WARRANTEIES, EXPRESSED OR IMPLIED, INCLUDING THE IMPLIED WARRANTEIES OF MARKET ABILITY AND FITNESS FOR PURPOSE. Sellers' and manufacturers' only obligation shall be to replace such quantity of the product proved to be defective. Before using, user shall determine the suitability of the product for its intended use, and user assumes all risks and liability whatsoever in connection therewith. NEITHER SELLER NOR MANUFACTURER SHALL BE LIABLE ETHER IN TORT OR IN CONTRACT FOR ANY LOSS OR DAMAGE, DIRECT, INCIDENTAL, OR CONSEQUENTIAL, INCLUDING LOSS OF PROFITS OR REVENUE ARISING OUT OF THE USE OR THE INABILITY TO USE A PRODUCT. No astrament nucristate order or recommendations by seller or purchaser not contained herein shall have any force or effect unless is statement, purchase order or recommendations by seller or purchaser not contained herein shall have any force or effect unless is an agreement signed by the officers of the seller and manufacturer. For more detail please refer to our website agreement si n·//www.tclad.c

All marks used above are trademarks and/or registered trademarks of TCLAD Inc. and its affiliates in the U.S., Germany and elsewhere.

© 2021 TCLAD Inc. All rights reserved.